

## SLIP RESISTANCE TEST REPORT

Client: Tile Warehouse Limited  
Client's Reference: 891070

Tested By: Dave Cockerton  
Date: 10 February 2015

### DESCRIPTION OF SAMPLE

Manufacturer: Niro Granite  
Common Name: Touchstone Smoked Grey  
Specimen Size: 600 x 600mm  
No. of Specimens Tested. 5

Material Type: Double Loaded Porcelain  
Surface Type: Structured  
Colour: Touchstone Smoked Grey  
Surface Coating: None

### METHOD

Tests were carried out in accordance with AS/NZS 3661.1 : 1993 Slip Resistance of Pedestrian Surfaces, Part 1- Requirements, Appendix A "Method for the Measurement of the Coefficient of friction of Wet Surfaces".

Type of Test: **Wet**

Location of Test: 19b Neil Park Drive

Air Temperature: °C21

East Tamaki

### RESULTS

Specimen No.	Dilution Ratio	Dwell Time	Mean Coefficient of Friction
one			0.44
two			0.44
three			0.45
four			0.45
five			0.45

**SAMPLE MEAN COEFFICIENT OF FRICTION: 0.45**

### REQUIREMENTS

**Horizontal Surfaces:** When tested in accordance with the method set out in Appendix A, the pedestrian surface shall have a mean coefficient of friction of not less than **0.40** and no specimen in that sample shall be less than **0.35**.

**COMMENTS:**

**SAFETY STEP (NZ) LTD**

THE ULTIMATE IN ANTI-SLIP AND WAY FINDING SYSTEMS