

SLIP RESISTANCE TEST REPORT

Client: Tile Warehouse Limited
Client's Reference: 890130

Tested By: Dave Cockerton
Date: 10 February 2015

DESCRIPTION OF SAMPLE

Manufacturer: JDD
Common Name: Babylon Dark Charcoal
Specimen Size: 150 x 900mm
No. of Specimens Tested. 5

Material Type: Glazed Porcelain
Surface Type: Matt
Colour: Babylon Dark Charcoal
Surface Coating: None

METHOD

Tests were carried out in accordance with AS/NZS 3661.1 : 1993 Slip Resistance of Pedestrian Surfaces, Part 1- Requirements, Appendix A "Method for the Measurement of the Coefficient of friction of Wet Surfaces".

Type of Test: **Wet**

Location of Test: 19b Neil Park Drive

Air Temperature: °C21

East Tamaki

RESULTS

Specimen No.	Dilution Ratio	Dwell Time	Mean Coefficient of Friction
one			0.37
two			0.37
three			0.36
four			0.35
five			0.36

SAMPLE MEAN COEFFICIENT OF FRICTION: 0.36

REQUIREMENTS

Horizontal Surfaces: When tested in accordance with the method set out in Appendix A, the pedestrian surface shall have a mean coefficient of friction of not less than **0.40** and no specimen in that sample shall be less than **0.35**.

COMMENTS:

SAFETY STEP (NZ) LTD

THE ULTIMATE IN ANTI-SLIP AND WAY FINDING SYSTEMS